

U S DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE		ATTORNEY'S DOCKET NUMBER OKAYAMA2
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371		U S APPLICATION NO (If known, see 37 CFR 1.5)
INTERNATIONAL APPLICATION NO. PCT/JP98/01198	INTERNATIONAL FILING DATE 19 March 1998	PRIORITY CLAIMED
TITLE OF INVENTION MATERIAL FOR AN APERTURE GRILLE FOR USE IN COLOR PICTURE...		
APPLICANT(S) FOR DO/EO/US H. OKAYAMA et al.		
<p>Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:</p> <ol style="list-style-type: none"> 1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. 2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. 3. <input checked="" type="checkbox"/> This is an express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1). 4. <input checked="" type="checkbox"/> A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date. 5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2)) <ol style="list-style-type: none"> a. <input type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau). b. <input checked="" type="checkbox"/> has been transmitted by the International Bureau. c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US). 6. <input checked="" type="checkbox"/> A translation of the International Application into English (35 U.S.C. 371(c)(2)). 7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)) <ol style="list-style-type: none"> a. <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau). b. <input type="checkbox"/> have been transmitted by the International Bureau. c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. d. <input checked="" type="checkbox"/> have not been made and will not be made. 8. <input type="checkbox"/> A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)). 9. <input type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). 10. <input type="checkbox"/> A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)). <p>Items 11. to 16. below concern document(s) or information included:</p> <ol style="list-style-type: none"> 11. <input type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98. 12. <input type="checkbox"/> An Assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included. 13. <input type="checkbox"/> A FIRST preliminary amendment. <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment. 14. <input type="checkbox"/> A substitute specification. 15. <input type="checkbox"/> A change of power of attorney and/or address letter. 16. <input checked="" type="checkbox"/> Other items or information: <ul style="list-style-type: none"> <input checked="" type="checkbox"/> Courtesy copy of the first page of the International Publication (WO 99/47719). <input checked="" type="checkbox"/> Courtesy Copy of the International Search Report. 		

SPECIFICATION

A MATERIAL FOR AN APERTURE GRILLE FOR USE IN A COLOR PICTURE TUBE AND A METHOD OF PRODUCING SAME, AND AN APERTURE GRILLE AND A COLOR PICTURE TUBE

BACKGROUND OF THE INVENTION

The present invention relates to a material for an aperture grille for use in a color picture tube, a producing method therefor, an aperture grille, and a color picture tube incorporating the aperture grille. More particularly, it relates to a material for an aperture grille for use in a color picture tube which has an excellent tensile strength and high temperature creep strength and besides good magnetic characteristics, and relates to a producing method therefor, an aperture grille made thereof, and a color picture tube incorporating this aperture grille.

When an aperture grille is incorporated into a color picture tube, it is welded to a frame of the color picture tube while being applied with a great tension. Therefore, a material for the aperture grille of the color picture tube essentially requires to have a tensile strength of at least 60 kgf/mm². Accordingly, the materials currently used for the aperture grille of the color picture tube comprise low carbon steel sheets, which have been reinforced by strengthening-forming.

Further, after welded to the frame of the color picture tube, the aperture grille is subjected to a heat treatment for blackening. This heat treatment is carried out at 455° C which is below the recrystallization temperature of steel for only a short time of about 15 minutes so that after blackening the tapes constituting the aperture grille may not be loosened but can be

maintained with its loaded tensile strength. However, under such heat treatment conditions for blackening, the tapes cannot be entirely free from a recovery phenomenon but involve elongation of it by the recovery, thereby suffering cuts and twists. For this reason, a material for an aperture grille for use in a color picture tube is required to have a tensile strength of not less than 60 kgf/mm² and a creep strength enough to cause no elongation even when subjected to such a heat treatment for blackening as conducted at a temperature of 455° C for a time of 15 minutes and to control its elongation of not more than 0.4% when the aperture grille is applied with a tensile strength of 30 kgf/mm².

The color picture tube comprises an electron gun and a luminescent screen which converts electron beam into picture images. The inside of the picture tube is covered with a magnetic shield member so as to prevent the electron beam from being biased by geomagnetism. The aperture grille also requires to be used as the magnetic shield member and, therefore, should be made of a material having a great magnetic flux density (Br) and a small coercive force (Hc) representing the magnetic characteristics, in other words, a material having a great ratio of magnetic flux density to coercive force (Br/Hc). However, such a low carbon steel sheet as mentioned above, which has been subjected to strengthening-forming for obtaining a high tensile strength and also subjected to the heat treatment for blackening at a temperature below its recrystallization temperature, has a small magnetic flux density of up to 8 kG and a great coercive force of about 5 Oe. Therefore, it is preferable in the present invention to use a material having a ratio of Br(kG) to Hc(Oe) exceeding 1.7.

So far, methods for improving tensile yield strength of a low carbon steel sheet include a solid solution strengthening

method by means of carbon and nitrogen. The more the carbon or the nitrogen increases in the steel, the more increases carbide or nitride so that the movement of ferromagnetic domain walls will be prevented, inducing the impairment of the magnetic characteristics of the steel. Besides, methods for improving creep strength of a low carbon steel sheet include that of precipitating carbide or others in the steel. These precipitates have mostly a large grain size in micron order, which prevent the movement of ferromagnetic domain walls, greatly impairing the magnetic characteristics of the steel. Therefore, this method has not been applied as a method of producing a material for an aperture grille for use in a color picture tube.

The present invention has an object to provide a material for an aperture grille for use in a color picture tube which has an excellent tensile strength and high temperature creep strength and superior magnetic characteristics to prior materials, and provide a producing method therefor, an aperture grille made thereof, and a color picture tube incorporating this aperture grille.

DISCLOSURE OF THE INVENTION

An invention as claimed in claim 1 relates to a material for an aperture grille for use in a color picture tube made of a low carbon steel sheet containing 9 to 30 wt% of Ni, and another invention as claimed in claim 2 relates to a material for an aperture grille for use in a color picture tube made of a low carbon containing 9 to 30 wt% of Ni and 0.1 to 5 wt% of Co.

An invention as claimed in claim 3 relates to a producing method of a material for an aperture grille for use in a color picture tube comprising the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni and annealing same at a

temperature of 400 to 500° C.

Another invention as claimed in claim 4 relates to a producing method of a material for an aperture grille for use in a color picture tube comprising the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni and 0.1 to 5 wt% of Co and annealing same at a temperature of 400 to 500° C.

Still another invention as claimed in claim 5 relates to a producing method of a material for an aperture grille for use in a color picture tube comprises the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni, subjecting same to process-annealing at a temperature of 500 to 800° C and another cold-rolling, and annealing same at a temperature of 400 to 500° C.

The other invention as claimed in claim 6 relates to a producing method of a material for an aperture grille for use in a color picture tube comprises the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni and 0.1 to 5 wt% of Co, subjecting same to process-annealing at a temperature of 500 to 800° C and another cold-rolling, and annealing same at a temperature of 400 to 500° C.

An invention as claimed in claim 7 relates to an aperture grille for use in a color picture tube, which is made of a low carbon steel sheet containing 9 to 30 wt% of Ni and another invention as claimed in claim 8 relates to an aperture grille for use in a color picture tube, which is made of a low carbon steel sheet containing 9 to 30 wt% of Ni and 0.1 to 5 wt% of Co.

An invention as claimed in claim 9 relates to a color picture tube incorporating an aperture grille made of a low carbon steel sheet containing 9 to 30 wt% of Ni and another invention as claimed in claim 10 relates to a color picture tube incorporating an aperture grille made of a low carbon steel sheet containing 9 to 30

wt% of Ni and 0.1 to 5 wt% of Co.

THE BEST MODE FOR CARRYING OUT THE INVENTION

It proved that a steel sheet having a tensile strength of not less than 90 kgf/mm² and good magnetic characteristics could be obtained by the present invention. Namely, the invention comprises the steps of cold-rolling a hot-rolled sheet consisting of a single phase α' (martensite) to which Ni, or Ni and Co are added, or cold-rolling a hot-rolled Ni-Fe alloy sheet or Ni-Co-Fe alloy sheet consisting of double phases of α' and γ (austenite) into a single phase α' at a reduction rate of not less than 60% by means of the strain-induced transformation, and annealing same at a temperature of 400 to 500° C.

The present invention is now described below in detail.

In the present invention, a material for an aperture grille for use in a color picture tube is preferably a low carbon steel sheet obtained by the step of subjecting the steel sheet to a decarburization and denitrification treatment by use of a vacuum degassing process to decrease the carbide and nitride in the steel sheet and accelerate the growth of crystal grains during hot-rolling and annealing. In addition, since the carbide and nitride finely dispersed in the steel prevent the movement of ferromagnetic domain walls to thereby deteriorate the magnetic characteristics of the steel, it is necessary to prescribe the elements included in the steel beforehand and reduce them to the least. Now the explanation begins with sorts and amounts of the elements to be added to the steel which is to be used for the material for the aperture grille for use in the color picture tube of the present invention.

As for C, the more the carbon exists in the steel sheet after

cold rolling, the more the carbide is produced to thereby prevent the movement of ferromagnetic domain walls and inhibit the growth of crystal grains, resulting in the impairment of the magnetic characteristics of the steel. For this reason, the upper limit of the addition amount of carbon is determined to be 0.01 wt%. The lower limit of the addition amount of carbon is desirably as little as it can be practically decreased through the vacuum degassing process.

As for Mn, manganese is essentially added to steel to react with sulfur in the steel so as to stabilize the sulfur as MnS, thus keeping the steel from the embrittlement during hot rolling. However, it is desirable for improving the magnetic characteristics of the steel to lessen the amount of manganese. So the addition amount of the manganese is limited up to 0.5 wt%.

As for Si, silicon acts to impair the adhesion properties of a black oxide film, so the addition amount of the silicon is limited up to 0.3 wt%.

As for S and N, the less sulfur and nitrogen are included in the steel, the better the growth of crystal grains can be accelerated, so the addition amount of the sulfur and nitrogen is desirably limited up to 0.01 wt%.

As for Ni, not less than 9 wt% of nickel is added to steel so that the steel structure after hot-rolling can attain a single α' (martensite) phase having a ferromagnetism as strong as possible and the highest strength. When the addition amount of nickel increases, a martensite starting temperature (M_s point) drops and when the nickel amount exceeds 20 wt%, the metal structure at the normal temperature will be changed into the double phase alloy of α' + austenite (γ). When the metal structure includes the γ phase, which is non-magnetic, its magnetic characteristics will be

impaired. However, even when the nickel amount exceeds 20 wt%, as far as less than 30 wt%, the metal structure has its γ phase changed into an α' phase through the strain-induced modification by means of cold-rolling at a reduction rate of not less than 60%. When the nickel amount exceeds 30 wt%, the γ phase is stabilized and even if the steel sheet is subjected to cold-rolling, the strain-induced modification no longer takes place, with the result that no single α' phase is attained. Therefore, the upper limit of the nickel amount is determined to be 20 wt%.

Cobalt is an element that hardly affects the martensite starting temperature (M_s point) and makes it easy to form a superlattice through a heat treatment in a temperature range from 400°C to 500°C. Thus, since cobalt effects an improvement in the tensile strength of the steel sheet as a material for a shadow mask, it is added thereto together with nickel. When the cobalt amount is less than 1.0 wt%, no effect can be obtained, and when more than 5 wt% of cobalt is added to the steel sheet, its coercive force increases so that B_r (kG) / H_c (Oe) decreases, which is now unfavorable as a magnetic shield material. Therefore, the cobalt amount is determined to be 1 to 5 wt%.

Next, a producing method of a thin steel sheet as a material for an aperture grille for use in a color picture tube of the present invention is explained.

The producing method comprises the steps of hot-rolling low carbon steel containing the above mentioned chemical components which has been subjected to a vacuum melting process or vacuum degassing process to be melted, pickling same to remove an oxide film formed during the hot-rolling, subsequently cold-rolling same at a reduction rate of not less than 60% to form a thin steel sheet of 0.035 to 0.2mm thickness; and annealing same at a temperature of 400

to 500°C. When the steel sheet is heated to a temperature of not less than 350°C, a super lattice of Ni-Fe or Ni-Fe-Co is formed in the steel sheet, where the magnetic flux density Br increases while the coercive force Hc decreases so that a value of Br/Hc increases.

When the steel sheet is heated to around 450°C, the value of Br/Hc comes to the maximum. When heated to a temperature in excess of 500°C, the steel sheet has its α' phase transformed into a non-magnetic γ phase so that the value of Br/Hc drastically drops, impairing its magnetic characteristics. Therefore, the annealing temperature is desirably within the range from 400°C to 500°C.

There may be another embodiment of the producing method of the present invention, which comprises the steps of hot-rolling the above mentioned low carbon steel sheet, pickling same, cold rolling same at a reduction rate of not less than 60% to form a steel sheet of 0.1~0.6mm thickness, subsequently subjecting same to process-annealing at a temperature of 500 to 800°C to control crystal grain sizes, subjecting same to another cold-rolling to form a thin steel sheet of 0.035 to 0.2mm thickness, and annealing same at a temperature of 400 to 500°C. When the process-annealing temperature is lower than 500°C, the steel sheet cannot be softened enough. On the other hand, when the process-annealing temperature is higher than 800°C, the steel sheet cannot attain a desired yield strength after it is subjected to the secondary cold-rolling and the above mentioned annealing.

[Examples]

The present invention is described more in detail with regard to examples below.

(Example 1)

Eight different kinds of low carbon steel (A~H) which respectively contain Ni, or Ni and Co as shown in Table 1 were vacuum-degassed and melted to prepare slabs, which were hot-rolled to form hot-rolled sheets each having a thickness of 2.5mm. These hot rolled sheets were subjected to sulfuric acid pickling and then cold rolling to form cold-rolled sheets each having a thickness of 0.1mm. Thereafter, they were annealed at temperatures as shown in Table 1. The thus obtained steel sheet samples were applied with 10 oersted of magnetic field using a compact type Epstein magnetism measuring apparatus to measure their magnetic flux densities and coercive forces and calculate values of $Br(kG)/Hc(Oe)$. The samples were also measured by use of TENSILON to obtain their tensile strengths, which are shown in Table 1.

(Example 2)

The same eight kinds of low carbon steel (A~H) which respectively contain Ni, or Ni and Co as shown in Example 1 were vacuum-degassed and melted to prepare slabs under the same conditions as in Example 1, which were hot-rolled to form hot-rolled sheets each having a thickness of 2.5mm. These hot-rolled sheets were subjected to sulfuric acid pickling and then cold rolling to form cold-rolled sheets each having a thickness of 0.3mm. Thereafter, they were subjected to process-annealing at a temperature of 750°C for a time of 40 minutes and another cold-rolling so as to have a thickness of 0.1mm each. Subsequently, they were annealed at temperatures as shown in Table 2. The thus obtained steel sheet samples were measured for the magnetic flux density and coercive force in the same manner as in Example 1 and calculated for the value of $Br(kG)/Hc(Oe)$. Further, they were measured for the tensile strength in the same manner as in

Example 1, which are shown in Table 2.

Table 1

(Table1)

Kind of Steel	Sample No.	Addition element(wt%)	Annealing temperature(°C)	Tensile strength(kg/mm ²)	Br/Hc (kG/Oe)	Division
A	A1	Ni(9)	400	110	2.4	Example
	A2		450	100	2.6	Example
	A3		500	95	2.8	Example
	A4		350	120	1.5	Comparative example
	A5		550	84	1.2	Comparative example
B	B1	Ni(15)	400	112	2.4	Example
	B2		450	104	2.6	Example
	B3		500	97	2.8	Example
	B4		350	123	1.6	Comparative example
	B5		550	89	1.2	Comparative example
C	C1	Ni(20)	400	115	2.6	Example
	C2		450	112	3.2	Example
	C3		500	101	2.3	Example
	C4		350	125	1.8	Comparative example
	C5		550	90	0.1	Comparative example
D	D1	Ni(25)	400	110	2.4	Example
	D2		450	100	3.9	Example
	D3		500	90	1.8	Example
	D4		350	115	1.5	Comparative example
	D5		550	90	0.1	Comparative example
E	E1	Ni(30)	400	100	2.8	Example
	E2		450	90	3.9	Example
	E3		500	85	1.6	Example
	E4		350	115	1.4	Comparative example
	E5		550	95	1.0	Comparative example
F	F1	Ni(20) Co(0.1)	400	117	2.4	Example
	F2		450	114	3.1	Example
	F3		500	103	2.1	Example
	F4		350	127	1.6	Comparative example
	F5		550	92	0.1	Comparative example
G	G1	Ni(20) Co(2)	400	120	2.3	Example
	G2		450	116	3.9	Example
	G3		500	103	1.6	Example
	G4		350	128	1.5	Comparative example
	G5		550	98	0.3	Comparative example
H	H1	Ni(20) Co(5)	400	125	2.0	Example
	H2		450	120	2.2	Example
	H3		500	115	2.8	Example
	H4		350	130	1.1	Comparative example
	H5		550	105	0.5	Comparative example

Table 2

(Table2)

Kind of Steel	Sample No.	Addition element(wt%)	Annealing temperature(°C)	Tensile strength(kg/mm ²)	Br/Hc (kG/Oe)	Division
A	A1	Ni(9)	400	105	2.5	Example
	A2		450	95	2.7	Example
	A3		500	90	3.0	Example
	A4		350	110	1.5	Comparative example
	A5		550	80	1.4	
B	B1	Ni(15)	400	109	2.6	Example
	B2		450	100	2.8	Example
	B3		500	92	3.1	Example
	B4		350	118	1.5	Comparative example
	B5		550	88	1.2	
C	C1	Ni(20)	400	113	2.6	Example
	C2		450	107	3.4	Example
	C3		500	103	2.8	Example
	C4		350	115	1.8	Comparative example
	C5		550	91	0.1	
D	D1	Ni(25)	400	110	2.4	Example
	D2		450	100	4.0	Example
	D3		500	90	1.8	Example
	D4		350	115	1.5	Comparative example
	D5		550	88	0.1	
E	E1	Ni(30)	400	98	2.8	Example
	E2		450	93	3.9	Example
	E3		500	82	1.6	Example
	E4		350	102	1.4	Comparative example
	E5		550	80	1.0	
F	F1	Ni(20) Co(0.1)	400	115	2.4	Example
	F2		450	109	3.2	Example
	F3		500	105	2.6	Example
	F4		350	117	1.6	Comparative example
	F5		550	93	0.1	
G	G1	Ni(20) Co(2)	400	117	2.4	Example
	G2		450	112	2.9	Example
	G3		500	106	2.9	Example
	G4		350	120	1.6	Comparative example
	G5		550	98	0.3	
H	H1	Ni(20) Co(5)	400	120	2.1	Example
	H2		450	116	2.3	Example
	H3		500	109	3.0	Example
	H4		350	125	1.3	Comparative example
	H5		550	105	0.4	

POSSIBLE USE IN THE INDUSTRIAL FIELD

The material for the aperture grille according to claim 1 comprises a low carbon steel sheet containing 9 to 30 wt% of Ni, and the material for the aperture grille according to claim 2 comprises a low carbon steel sheet containing 9 to 30 wt% of Ni and 0.1 to 5 wt% of Co. Therefore, they are excellent in the magnetic characteristics and strength.

The producing method of the material for the aperture grille according to claim 3 comprises the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni and annealing same at a temperature of 400 to 500°C, the producing method of the material for the aperture grille according to claim 4 comprises the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni and 0.1 to 5 wt% of Co and annealing same at a temperature of 400 to 500°C, the producing method of the material for the aperture grille according to claim 5 comprises the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni, subjecting same to process-annealing at a temperature of 500 to 800°C and another cold-rolling, and annealing same at a temperature of 400 to 500°C, and the producing method of the material for the aperture grille according to claim 6 comprises the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni and 0.1 to 5 wt% of Co, subjecting same to process-annealing at a temperature of 500 to 800°C and another cold-rolling, and annealing same at a temperature of 400 to 500°C. Consequently, using these methods of the present invention, it is possible to obtain the materials for the aperture grille for use in the color picture tube having an excellent tensile strength of not less than 90 kgf/mm², and good magnetic characteristics as represented by the value of Br (kG)/Hc(Oe) exceeding 1.7.

What is claimed is:

1. A material for an aperture grille for use in a color picture tube made of a low carbon steel sheet containing 9 to 30 wt% of Ni.

2. A material for an aperture grille for use in a color picture tube made of a low carbon steel sheet containing 9 to 30 wt% of Ni and 0.1 to 5 wt% of Co.

3. A method of producing a material for an aperture grille for use in a color picture tube as claimed in claim 1, comprising the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni and annealing same at a temperature of 400 to 500° C.

4. A method of producing a material for an aperture grille for use in a color picture tube as claimed in claim 2, comprising the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni and 0.1 to 5 wt % of Co and annealing same at a temperature of 400 to 500° C.

5. A method of producing a material for an aperture grille for use in a color picture tube as claimed in claim 1, comprising the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni, subjecting same to process-annealing at a temperature of 500 to 800° C and another cold-rolling, and annealing same at a temperature of 400 to 500° C.

6. A method of producing a material for an aperture grille for use in a color picture as claimed in claim 2, comprising the steps of cold-rolling a low carbon steel sheet containing 9 to 30

wt% of Ni and 0.1 to 5 wt% of Co subjecting same to process-annealing at a temperature of 500 to 800°C and another cold-rolling, and annealing same at a temperature of 400 to 500°C.

7. An aperture grille for use in a color picture tube, which is made of a low carbon steel sheet containing 9 to 30 wt% of Ni.

8. An aperture grille for use in a color picture tube, which is made of a low carbon steel sheet containing 9 to 30 wt% of Ni and 0.1 to 5 wt% of Co.

9. A color picture tube incorporating an aperture grille for use in a color picture tube, which is made of a low carbon steel sheet containing 9 to 30 wt% of Ni.

10. A color picture tube incorporating an aperture grille for use in a color cathode ray tube, which is made of a low carbon steel sheet containing 9 to 30 wt% of Ni and 0.1 to 5 wt% of Co.

ABSTRACT

The object of the present invention is to provide a material for an aperture grille for use in a color picture tube, which has an excellent yield strength, high temperature creep strength and superior magnetic characteristics to prior materials and provide a producing method therefor, an aperture grille made thereof and a color picture tube incorporating the aperture grille. In order to achieve the object mentioned above, the method of the present invention comprises the steps of cold-rolling a low carbon steel sheet containing 9 to 30 wt% of Ni, or 9 to 30 wt% of Ni and 0.1 to 5 wt% of Co; and annealing the cold-rolled steel sheet at a temperature of 400 to 500°C. Alternatively, the method comprises the steps of: cold-rolling the low carbon steel sheet same as mentioned above; subjecting the cold-rolled steel sheet to process-annealing at a temperature of 500 to 800°C and another cold-rolling; and thereafter annealing same.

1401 PCT-US

Page 2 of 2 Pages

Atty. Docket: OKAYAMA2

Title: MATERIAL FOR AN APERTURE GRILLE FOR USE IN A COLOR PICTURE TUBE

U.S. Application filed _____ Serial No. _____
PCT Application filed _____ Serial No. _____

I hereby further declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. §1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

1-1 FULL NAME OF FIRST INVENTOR Hironao OKAYAMA		INVENTOR'S SIGNATURE <i>Hironao Okayama</i>	DATE December 5, 2000
RESIDENCE Yamaguchi, Japan <i>SPX</i>		CITIZENSHIP Japanese	
POST OFFICE ADDRESS c/o TOYO KOHAN Co., Ltd., Technical Research Laboratory, 1296-1, Higashitoyoi, Kudamatsu-shi, Yamaguchi, 744-8611 Japan			
2-0 FULL NAME OF SECOND JOINT INVENTOR Tsuneyuki IDE		INVENTOR'S SIGNATURE <i>Tsuneyuki Ide</i>	DATE December 28, 2000
RESIDENCE Yamaguchi, Japan <i>SPX</i>		CITIZENSHIP Japanese	
POST OFFICE ADDRESS c/o TOYO KOHAN Co., Ltd., Technical Research Laboratory, 1296-1, Higashitoyoi, Kudamatsu-shi, Yamaguchi, 744-8611 Japan			
3-0 FULL NAME OF THIRD JOINT INVENTOR Yasuo TAHARA		INVENTOR'S SIGNATURE <i>Yasuo Tahara</i>	DATE December 5, 2000
RESIDENCE Yamaguchi, Japan <i>SPX</i>		CITIZENSHIP Japanese	
POST OFFICE ADDRESS c/o TOYO KOHAN Co., Ltd., Technical Research Laboratory, 1296-1, Higashitoyoi, Kudamatsu-shi, Yamaguchi, 744-8611 Japan			
4-0 FULL NAME OF FOURTH JOINT INVENTOR Hiroshi FUJISHIGE		INVENTOR'S SIGNATURE <i>Hiroshi Fujishige</i>	DATE December 5, 2000
RESIDENCE Yamaguchi, Japan <i>SPX</i>		CITIZENSHIP Japanese	
POST OFFICE ADDRESS c/o TOYO KOHAN Co., Ltd., Technical Research Laboratory, 1296-1, Higashitoyoi, Kudamatsu-shi, Yamaguchi, 744-8611 Japan			
5-0 FULL NAME OF FIFTH JOINT INVENTOR Akira IKEDA		INVENTOR'S SIGNATURE <i>Akira Ikeda</i>	DATE December 28, 2000
RESIDENCE Yamaguchi, Japan <i>SPX</i>		CITIZENSHIP Japanese	
POST OFFICE ADDRESS c/o TOYO KOHAN Co., Ltd., Technical Research Laboratory, 1296-1, Higashitoyoi, Kudamatsu-shi, Yamaguchi, 744-8611 Japan			
6-0 FULL NAME OF SIXTH JOINT INVENTOR Seisuo TAKAKI		INVENTOR'S SIGNATURE <i>Seisuo Takaki</i>	DATE December 21, 2000
RESIDENCE Fukuoka, Japan <i>SPX</i>		CITIZENSHIP Japanese	
POST OFFICE ADDRESS c/o KYUSHU UNIVERSITY Faculty of Engineering, 10-1, Hakozaki 6-chome, Higashi-ku, Fukuoka-shi, Fukuoka, 812-0053 JAPAN			
FULL NAME OF SEVENTH JOINT INVENTOR		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			